


ENDURE[®] E37 carbon black



GENERAL DESCRIPTION

Many industrial rubber product applications operate under severe conditions that lead to significant wear and tear. Improved durability of the rubber components may provide a distinct total cost advantage. As part of our ongoing commitment to deliver solutions that meet our customers' needs, we have developed the ENDURE[®] family of carbon blacks engineered for durability.

Improving wear, chunking and tear resistance or reducing heat buildup can result in longer part life, reducing costly equipment downtime, increasing throughput and enhancing end user profitability. Our products can enhance rubber part life and durability by optimizing the balance between heat buildup and reinforcement and are identified by the letter "D" in the ENDURE nomenclature system.

In certain applications such as conveyor belts, reduced hysteresis in the rubber compound may also be of interest as it can result in decreased power consumption, representing a significant energy and operating cost saving. In other applications such as rubber tracks and certain mill liners, a decrease in hysteresis can help with extending part life. Cabot products can help reduce energy costs and part life by optimizing the balance between hysteresis and reinforcement and are identified by the letter "E" in the ENDURE nomenclature system.

PERFORMANCE FEATURES

ENDURE[®] E37 carbon black provides low hysteresis and is relatively easy to disperse with fast incorporation and good dispersion. ENDURE E37 carbon black offers reinforcement similar to compounds made with ASTM N300 series carbon blacks but with a considerable reduction in hysteresis and significantly greater durability than ASTM N500 series carbon blacks.


TYPICAL APPLICATIONS

- ◆ Bottom cover of low rolling resistant conveyor belts
- ◆ Base of rubber tracks
- ◆ Tread of rubber tracks

ENDURE[®] E37 carbon black

TECHNICAL DATA

ENDURE E37 carbon black can reduce the hysteresis of rubber compounds compared to compounds made with ASTM N300 series carbon blacks, maintain good reinforcement properties and exhibit improved durability over N500 series carbon blacks.



50/50 NR/BR Formulation	ASTM N330	ASTM N550	ENDURE [®] E37 CB
Loading (phr)	53	56	50
Hardness (Shore A)	68	67	68
Tensile Strength (MPa)	20.5	19.8	21.2
100% Mod (MPa)	3.7	4.1	4.3
300% Mod (MPa)	16.9	16.7	18.8
Elongation at Break (%)	351	340	339
Tear Strength (N/mm)	86	40	67
DIN Abrader (mm ³)*	66	88	76
Rebound @23 °C (%)	60	70	65
Tan δ max @25 °C	0.16	0.11	0.13
RR Factor	0.083	0.069	0.070

* higher DIN Abrader means worse

For information on product-specific storage conditions, please refer to the applicable Safety Data Sheet (SDS) available from your Cabot Cabot representative or at cabotcorp.com/contact

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

The ENDURE[®] brand is a registered trademark of Cabot Corporation.

©2025 Cabot Corporation. All rights reserved worldwide. ENE37_pds 12/2025