

## PLASBLAK® PE1371 BLACK MASTERBATCH

### Product highlights

PLASBLAK PE1371 black masterbatch is designed for high quality packaging and agricultural films requiring enhanced protection against UV light degradation. It can also be used in general extrusion, molding and cable sheathing applications.

This product is suitable for use in a wide range of plastics that come into contact with food. For more details regarding the food contact compliance in various countries, please refer to the relevant Food Contact Statement available from your usual Cabot representative.



### Method of addition

PLASBLAK PE1371 black masterbatch is designed for ease of dilution and homogeneous mixing and is therefore suitable for direct addition using automatic dosing units or by pre-blending.

### Addition rate

The amount of masterbatch added depends on the performance requirements of the final application. Typical addition rates can range from 2% to 7% masterbatch.

TYPICAL PROPERTIES			
PROPERTY	TYPICAL VALUE	UNITS	TEST METHOD
Carrier	LDPE	-	-
Pigment	40% P-type carbon black	-	-
Compatibility	LDPE, LLDPE, HDPE, PP, ethylene copolymers	-	-
Density @ 23°C	1140	kg/m <sup>3</sup>	ISO 1183
MFI 21.6 kg/190°C	27	g/10 min	ISO 1133

The data in the table above are typical test values intended as guidance only and are not product specifications. Product specifications are available upon request from your Cabot representative.

# PLASBLAK® PE1371 BLACK MASTERBATCH

## Impact on physical properties of LDPE

The addition of 6.25% PE1371 black masterbatch to the LDPE resin to produce a compound with 2.5 wt% carbon black has no significant influence on the properties of the base resin.

PROPERTY	TEST METHOD	UNIT	NATURAL LDPE	LDPE + 6.25% PE1371
Density @ 23°C	ISO 1183	kg/m <sup>3</sup>	925	934
Vicat softening point	ISO 306	°C	94	93
MFI 21.6 kg/190°C	ISO 1133	g/10 min	2.3	2.4
Tensile strength at break	ISO R527	MPa	15.1	14.7
Tensile strength at yield	ISO R527	MPa	10.3	10.9
Elongation at break	ISO R527	%	530	530

## Product form and logistics

- ◆ Product form: pellets or in micro-pulverized form under product code PM1371
- ◆ Regional availability: global
- ◆ Packaging options: 25 kg bags

For information on product-specific storage conditions, please refer to the applicable Safety Data Sheet (SDS) available from your Cabot representative or at [cabotcorp.com](http://cabotcorp.com).

The PLASBLAK name is a registered trademark of Cabot Corporation.

### NORTH AMERICA

Cabot Plastics Canada  
707 Pierre Tremblay Boulevard  
Saint-Jean-sur-Richelieu  
QC, J2X 5G5  
Canada  
T +1 450 347 4371  
F +1 450 347 9936

### SOUTH AMERICA

Cabot Brasil Industria e Comercio Ltda.  
Rua do Paraíso 148 - 5º andar  
04103-000 São Paulo  
Brazil  
T +55 11 2144 6400  
F +55 11 3253 0051

### EUROPE

SIA Cabot Latvia  
74A Gustava Zemgala gatve  
LV- 1039 Riga  
Latvia  
T +371 670 50 900  
F +371 670 50 985

### MIDDLE EAST/AFRICA

Cabot Specialty Chemicals  
Jebel Ali Free Zone  
LOB 15, Office 424, Dubai  
United Arab Emirates  
T +971 4 8871 800  
F +971 4 8871 801

### ASIA PACIFIC

Cabot China Ltd.  
558 Shuangbai Road  
Minghang District  
Shanghai 201108  
China  
T +86 21 5175 8800  
F +86 21 6434 5532

### JAPAN

Cabot Specialty Chemicals, Inc.  
Sumitomo Chiba-Daimon Bldg, 3F  
2-5-5 Shiba Daimon,  
Minato-ku, Tokyo 105-0012  
Japan  
T +81 6820 0255  
F +81 3 5425 4500

The data and conclusions contained herein are based on work believed to be reliable, however, Cabot cannot and does not guarantee that similar results and/or conclusions will be obtained by others. This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.