

SPECIALTY CARBON BLACKS

VULCAN® XC72 Conductive Carbon Black



Product Highlights

VULCAN XC72 specialty carbon black is a uniquely designed conductive carbon black from our XC family of conductive carbon blacks. Its unique properties allow end products to deliver functionality at relatively lower loading levels compared to Cabot's other carbon blacks in the XC family. VULCAN XC72 specialty carbon black has demonstrated its performance capabilities for many years, allowing compounders to feel confident using it in a wide range of conductive applications.

Key Applications

VULCAN XC72 specialty carbon black is suitable for use across a range of conductive applications:

- Conductor shields used in medium voltage power cables
- Insulation shields used in medium voltage power cables
- Conductive plastic molded or extruded parts where protection from electrostatic discharge (ESD) is required

By compounding VULCAN XC72 specialty carbon black into plastics, a compounder can change the electrical property of the final product from insulative to conductive, anti-static, or dissipative. For instance, VULCAN XC72 specialty carbon black is compounded into plastics trays and pouches that are used extensively in electronics manufacturing to protect sensitive products against electrostatic discharge. In addition, it is frequently compounded in molded or extruded parts to help deliver dissipative performance in hazardous environments.


Performance Features

VULCAN XC72 specialty carbon black has several important features:

- A full range of conductivity performance depending on loading (but typically at lower loadings than other XC carbon blacks or standard carbon blacks)
- Good dispersion characteristics to promote surface smoothness and preserve mechanical performance of polymer
- Low sulfur and grit levels



VULCAN® XC72 Conductive Carbon Black






Figure 2:

EEA Compound with 38% Loading of Carbon Black

Typical Properties		
PROPERTY	VALUES	TEST METHOD
lodine number (mg/g)	253	ASTM D-1510
OAN (cc/100g)	174	ASTM D-2414
325 mesh residue (ppm)	(25	ASTM D-1 514
Density (kg/m3)	264	ASTM D-1513

The data in the table above are typical test values intended as guidance only, and are not product specifications. Product specifications are available upon request from your Cabot representative.

Product Form & Logistics

- Product Form: Pellets or fluffy
- Regional Availability: Global
- Bag Packaging Options: 15 kg paper
- Bulk Packaging Options: 750 kg FIBC

The Material Safety Data Sheet (MSDS) available through your Cabot representative or on our website www.cabotcorp.com provides the recommended storage conditions of this product.



NORTH AMERICA Cabot Corporation Business and TechnIcal Center 157 Concord Road Billerica, MA 01821-7001

TEL +1 800 462 2313 FAX +1 978 670 7035

SOUTH AMERICA

Cabot Latin American Division Rue do Paraiso, 148 -5° ander 04103-000, Sao Paolo,

SP BRAZIL TEL +55 11 2144 6400 FAX +55 11 3253 0051

EUROPE

SIA Cabot Latvia 74A Gustava Zemgala gatve Riga, LV-1039, LATVIA

TEL +371 6705 0900 FAX +371 6705 0985

MIDDLE EAST/AFRICA

Cabot Specialty Chemicals Jebel Ali Free Zone LOB 15, Office 424 Dubai

UNITED ARAB EMIRATES **TEL** +971 4 8871 800 **FAX** +971 4 8871 801

ASIA PACIFIC

ASIA PACIFIC
Cabot China Ltd.
558 Shuangbai Road
Shanghai 201108,
CHINA

TEL +86 21 5175 8800 FAX +86 21 6434 5532

JAPAN

Cabot Specialty Chemicals, Inc. Sumitomo Chiba-Daimon Bldg. 3 F 2-5-5 Shiba Daimon, Minato-ku, Tokyo 105-0012, 1APAN

TEL +81 3 6820 0255 FAX +81 3 5425 4500

The data and conclusions contained herein are based on work believed to be reliable, however, Cabot cannot and does not guarantee that similar results and/or conclusions will be obtained by others. This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.